



September 15th, 2000  
Supersedes November 11th, 1999

**0040/292 TECHNICAL INFORMATION SHEET**

	<u>IMPERIAL</u>	<u>METRIC</u>	
<b>Construction: (per inch)</b>			<b>ASTM D-3775</b>
<b>(per 10cm)</b>			
<b>Warp:</b>	<b>6.0</b>	<b>24</b>	
<b>Weft:</b>	<b>5.9</b>	<b>23</b>	
<b>Weight: (oz/yd<sup>2</sup>)</b>	<b>4.5</b>	<b>152</b>	<b>ASTM D-3776</b>
<b>(g/m<sup>2</sup>)</b>			
<b>Weave:</b>		<b>Leno</b>	
<b>Finish:</b>		<b>Alkali Resistant</b>	
<b>Thickness: (per inch)</b>	<b>0.016</b>	<b>0.40</b>	<b>ASTM D-1777</b>
<b>(per mm)</b>			
<b>Minimum Tensile: (lb/in)</b>			<b>ASTM D-5035</b>
<b>(N/2.54cm)</b>			
<b>Warp:</b>	<b>150</b>	<b>665</b>	
<b>Weft:</b>	<b>200</b>	<b>890</b>	
<b>Hand:</b>		<b>Soft</b>	

All statements herein are expressions of opinion which we believe to be accurate and reliable but are presented without guarantee or responsibility on our part. Statements concerning possible use of our product are not intended as recommendations for their use in the infringement of any patent. No patent warranty of any kind, express or implied, is made or intended.

Values presented above are nominal and only to be used as guidelines.